

# COSMO CA-500.110

\*\*\* COSMOPLAST 500

## Cyanoacrylate - Fast-Setting Adhesive

### Examples for Application

- Sewage technique
- Sealing technique
- Electrical / electronic industry
- EPDM seals in window, façade, and vitrine construction
- Vehicle / shipbuilding
- Household appliances production
- Plastics / elastomer / rubber processing
- Leather / shoe industry
- Medical / dental technology, orthopaedics
- Metal construction / technical industrial supplies
- Jewellery industry
- Optical goods industry
- Toy industry
- Advertising techniques / advertising industry
- Exhibition stand construction

### Special Properties

- locks
- bonds within seconds
- Short time to reach functional strength for assembly works
- Good adhesion characteristics to different surfaces
- Solvent-free
- Good wetting of the substrate
- Hard adhesive joint
- Extremely short fixing times
- Very high strengths
- Good UV-stability
- Highly frost- and heat-resisting

### Technical Data

**Basis:** Modified cyanoacrylates

#### Viscosity

measured by cone and plate (3 000 s<sup>-1</sup>) at +25 °F (+77 °F) approx. 20 mPa.s (20 cP)

#### Density

as per EN 542 at +20 °C (+68 °F) approx. 1.05 g/cm<sup>3</sup> (8.76 lb/gal)

#### Functional hardness



Weiss USA LLC  
2213 Stafford St Ext., USA Monroe, NC 28111  
Telephone: 704 282 4496, <http://www.weiss-usa.com>

# COSMO CA-500.110

\*\*\* COSMOPLAST 500

## Cyanoacrylate - Fast-Setting Adhesive

EPDM/EPDM - profile sealing	approx. 4 s
PVC rigid/PVC rigid	from 8 s
<hr/>	
<b>Gap bridging</b>	Max. 0.1 mm (3.9 mil)
<hr/>	
<b>Curing time</b>	
at +20 °C (+68 °F), 50% r. H.	approx. 16 h
<hr/>	
<b>Softening range</b>	from +80 °C (+176 °F)

### Instructions for use

The surfaces of the workpieces to be bonded must be dry, and free from dust and grease.

Apply the adhesive from the trading unit or by means of a CA-dosing unit onto one side.

Immediately after application, the workpieces must be fit together and pressed until they reach the required functional strength.

In principle, CA-adhesives cure by means of air and material humidity. This means that ambient conditions, material and condensation humidity on the surfaces to be glued, thickness of applied adhesive layer and press power, as well as surface roughness of the materials to be glued significantly influence the process.

The chemical characteristics of the surfaces to be glued, e.g. pH-value, variations of raw material characteristics, surface coatings, as well as corrosion and contamination have a significant effect on the desired bonding strength.

Pressing times strongly depend on material and adhesive temperature.

To reduce the pressing times, or to accelerate curing of cyanoacrylate adhesives in thicker bonded joints >0.10 mm (3.9 mil), the accelerator COSMO SP-860.120 is to be used.

To achieve a durable resistance to penetration of rain, the ift-Rosenheim recommends additional bonding of the section corner on the glass pane using neoprene rubber filler or sealing compound for bonding the external glass strip seals in window construction.

If silicon, TPE sections and polyolefins are bonded, they are to be pretreated with primer COSMO SP-840.110. The variety of materials requires to carry out some preliminary tests yourself.

Bonding of aluminium, copper, brass: only on chemically pretreated or varnished surfaces; these materials cannot be durably bonded to be age-resistant without appropriate pre-treatment of the surfaces to be glued.

Bonding of materials with different longitudinal extension must be assessed regarding their long-term behaviour, especially when they are exposed to fluctuating temperature ranges.

Please, consider the relevant Technical Data Sheets of the recommended products mentioned above.

*Open time, as well as the necessary pressing time, can only be determined accurately by self-tests because they are strongly influenced by material characteristics, temperature, applied quantity, air humidity, material humidity, thickness of adhesive film, press power, and other criterions. Usually, appropriate safety factors are considered for the guiding values.*

### Important instructions

Only instructed personnel in specialist firms are allowed to use the product!

KEEP OUT OF REACH OF CHILDREN !

KEEP HOBBOCK, DRUM, CONTAINER, e.g. TIGHTLY CLOSED !



Weiss USA LLC  
2213 Stafford St Ext., USA Monroe, NC 28111  
Telephone: 704 282 4496, <http://www.weiss-usa.com>

# COSMO CA-500.110

\*\*\* COSMOPLAST 500

## Cyanoacrylate - Fast-Setting Adhesive

USE ONLY FOR APPLICATIONS MENTIONED IN THE TECHNICAL DATA SHEET !

NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. WEISS USA LLC SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

Our user instructions, processing guidelines, product- and performance data, and other technical statements are only general directives; they describe only the condition of our products (values, determination of values on the date of completion) and the performances do not represent a warranty in the sense of § 443 BGB. **Because of the wide variety of applications of the individual product and the relevant special conditions (e. g. processing parameters, material characteristics, etc.), it is up to the user to test it itself;** our free expert advice for application provided in speech, writing, and as test is nonbinding.

*Please, also consider the Safety Data Sheet!*

### Cleaning

Remove the fresh, not cured adhesive from the surfaces and the tools using COSMO CL-300.150.

Cured adhesive can only be removed mechanically.

### Storage

Store original packagings tightly closed, dry without direct sun radiation.

Optimum storage at temperatures from +2 °C (+36 °F) to +8 °C (+46 °F).

Storage life in unopened original packagings at temperatures from +15 °C (+59 °F) to +25 °C (+77 °F): 12 Months.

During the storage time, viscosity is increasing, reactivity is decreasing.

### Packaging

PE-bottle, net weight: 20 g (0.71 oz)

PE-bottle, net weight: 50 g (1.76 oz)

PE-bottle, net weight: 500 g (17.6 oz)

Other trading units on request.

### Accessories

COSMO SP-810.110 – CA-capillaries

COSMO SP-860.120 – CA-accelerator in aerosol can

COSMO SP-840.110 – CA-primer for polyolefins



Weiss USA LLC  
2213 Stafford St Ext., USA Monroe, NC 28111  
Telephone: 704 282 4496, <http://www.weiss-usa.com>

made by weiss